

DURO-LAST® PITCH PAN FILLER

DESCRIPTION:

Duro-Last® Pitch Pan Filler is an easy flowing, self-leveling sealant for use in pitch pans. The sealant is UV and impact resistant, and is formulated for adhesion to most types of building materials. The high tack ensures a weather-tight seal around penetrations. It is excellent for use in areas subjected to stress and vibration as well as to expansion and contraction.

ORDERING:

Pitch Pan Filler is supplied in 10.1-fluid-ounce (298.7-mL) cartridges, which can be ordered individually or in cases of 30.

One cartridge will cover approximately 18 in.³ (295 cm³).

- 10.1-fluid ounce (298.7-mL) cartridge white (Item #11222)

STORAGE AND HANDLING:

- Always store in a dry location protected from the elements.
- Shelf life is 12 months in an unopened tube at or below 80° F (27° C).

PRECAUTIONS:

- Read Safety Data Sheets (SDS) prior to using.
- Wear proper personal protective equipment, such as gloves and eye protection, per the SDS.
- **Keep away from children.**
- Use with adequate ventilation. Inhalation of vapor during application and cure may cause slight eye or throat irritation.
- In case of contact with eyes, lips, or mouth, flush thoroughly with water. If irritation persists, consult a physician.
- Prolonged contact with skin may cause mild irritation. Avoid repeated, prolonged contact with skin.

INSTALLATION:

- Requirements
 - Apply to clean, dry surfaces free of contaminants (oils, greases, coatings, etc.) that can adversely affect adhesion.
 - Do not apply to surfaces that bleed oils or solvents.
 - Product is not paintable.
 - Product does not adhere to Kynar®-coated metal or asphalt materials.
 - Product must not come into contact with surfaces that exceed 120° F (49° C).
A 1-inch (25-mm) air gap is required.

- Pitch pans must be constructed of sheet metal, wood, PVC pipe or similar, rigid, construction material. Duro-Last PVC-coated metal pitch pans and Duro-TECH™ TPO-coated metal pitch pans are recommended.
- Fill the pitch pan up to 1/2 inch (13 mm) from the top ledge with material such as mortar, concrete, or insulation. Take precautions to prevent the Pitch Pan Filler from migrating through the filler material.
- Apply Pitch Pan Filler using a standard caulking gun. Fill the entire top with a minimum 1/2 inch (13-mm) thickness of sealant.
- Water must not be allowed to pond within the pitch pan. Cover with approved Duro-Last caulk and slope to the outside of the pitch pan.
- Use mineral spirits for cleanup.
- Refer to Details 4000 for PVC and 4000T for TPO and follow the complete installation instructions.



PHYSICAL PROPERTIES	
Volume	18 in. ³ (294 cm ³)
Texture	Smooth
Color	White
Application Temperature Range	0 – 120° F (-18 – 49° C) ambient air
Skin Time	20 – 45 minutes
Cure Time	24 – 48 hours
Odor	Mild
Shrinkage	None
Low Temperature Flexibility	Retained to -40° F (-40° C)
Staining	Non-staining
UV Ratings (ASTM G-151)	No change in appearance or physical properties after 2,000 hours UV-A
Solubility	Insoluble in water
	Soluble in most organic solvents