

# DURO-LAST® PITCH PAN FILLER

## DESCRIPTION:

Duro-Last® Pitch Pan Filler is an easy flowing, self-leveling sealant for use in pitch pans. The sealant is UV and impact resistant, and is formulated for adhesion to most types of building materials. The high tack ensures a weather-tight seal around penetrations. It is excellent for use in areas subjected to stress and vibration as well as to expansion and contraction.

## ORDERING:

Pitch Pan Filler is supplied in 10.1-ounce cartridges and can be ordered individually or in cases of 30. One cartridge will cover approximately 18 cubic inches.

- 10.1-ounce cartridge white (Item #11222)

## STORAGE AND HANDLING:

- Always store in a dry location protected from the elements.
- Shelf life is 12 months in an unopened tube at or below 80° F (26° C).

## PRECAUTIONS:

- Read Safety Data Sheets (SDS) prior to using.
- Wear proper personal protective equipment, such as gloves and eye protection, per the SDS.
- **Keep away from children.**
- Use with adequate ventilation. Inhalation of vapor during application and cure may cause slight eye or throat irritation.
- In case of contact with eyes, lips, or mouth, flush thoroughly with water. If irritation persists, consult a physician.
- Prolonged contact with skin may cause mild irritation. Avoid repeated, prolonged contact with skin.

## INSTALLATION:

- Requirements
  - Apply to clean, dry surfaces free of contaminants (oils, greases, coatings, etc.) that can adversely affect adhesion.
  - Do not apply to surfaces that bleed oils or solvents.
  - Product is not paintable.

- Product does not adhere to Kynar®-coated metal or asphalt materials.
  - Product must not come into contact with surfaces that exceed 120° F. A 1-inch air gap is required.
- Pitch pans must be constructed of sheet metal, wood, PVC pipe or similar, rigid, construction material. Duro-Last vinyl-coated metal pitch pans are recommended.
  - Fill the pitch pan up to ½ inch of the top ledge with material such as mortar, concrete or insulation. Take precaution to prevent the Pitch Pan Filler from migrating through the filler material.
  - Apply Pitch Pan Filler using a standard caulking gun. Fill the entire top with a minimum ½ inch thickness of sealant.
  - Water must not be allowed to pond within the pitch pan. Cover with approved Duro-Last caulk to slope to the outside of the pitch pan.
  - Use mineral spirits for cleanup.
  - Refer to Detail Drawings 4030, 4040 and 4045 for complete installation instructions.



TABLE 1. PHYSICAL PROPERTIES

Volume	18 in. <sup>3</sup> (294 cm <sup>3</sup> )
Texture	Smooth
Color	White
Application Temperature Range	0 – 120° F (-17 – 48° C) ambient air
Skin Time	20 – 45 minutes
Cure Time	24 – 48 hours
Odor	Mild
Shrinkage	None
Low Temperature Flexibility	Retained to -40° F (-40° C)
Staining	Non-staining
UV Ratings (ASTM G-151)	No change in appearance or physical properties after 2,000 hours UV-A
Solubility	Insoluble in water
	Soluble in most organic solvents