

DURO-FLEECE PLUS® 60-MIL MEMBRANE

ADVANTAGES:

Duro-Last® Duro-Fleece Plus® 60-Mil (DFP60) is an excellent choice for projects requiring a long lasting, energy efficient roofing membrane. The combination of fleece and the proven performance of Duro-Last roofing membrane results in an ideal product for use in adhered and mechanically fastened applications over a wide variety of roof substrates. A complete line of custom-fabricated accessories is available for use with DFP60.

DESCRIPTION:

In addition to the fleece, DFP60 incorporates a weft-inserted, knitted scrim within PVC films to provide exceptional strength and waterproofing.

PVC Film – Proprietary thermoplastic PVC formulation of resins, plasticizers, stabilizers, biocides, flame retardants, and U.V. absorbents.

- PVC film above weft-inserted scrim – 32 mil, nominal

Weft-Inserted Scrim – An 18 x 14 polyester fabric construction with weft insertion provides superior tear and puncture resistance. The polyester thread is treated to prevent wicking.

Fleece – The 5.5-ounce per square yard needle-punched polypropylene fleece provides excellent properties for adhering to, or mechanically fastening over, a variety of substrates. Each roll of membrane has one selvage edge where the fleece is held back 2.25 inches to provide for hot-air welding to the underlying membrane.

Total Membrane Thickness – 60 mil, nominal

Overall Thickness (with Fleece) – 90 mil, nominal

Weight – 0.40 lb/ft²

Color – White

R-Value – 0.1 R (0.1 ft²·°F·hr/Btu)

Packaging – DFP60 is supplied in the roll sizes shown below. A full pallet contains ten rolls.

ROLL DIMENSIONS		
Dimensions	Approximate Coverage	Approximate Weight
120 in. x 100 ft	975 ft ²	400 lb
60 in. x 100 ft	475 ft ²	200 lb

¹ Assuming 3-inch overlap

Overlap Line – A line, 6 inches from one edge of the sheet, is factory-applied to the top of the sheet to assist in maintaining proper overlap between sheets.



ENERGY EFFICIENCY:

White DFP60 is an excellent product for complying with California Title 24, LEED® and other energy efficiency programs requiring the use of a highly reflective roof membrane.

COOL ROOF RATING COUNCIL (CRRC)							
Color	CRRC ID	Solar Reflectance		Thermal Emittance		Solar Reflective Index (SRI)	
		Initial	3-yr	Initial	3-yr	Initial	3-yr
White	0610-0017	0.87	0.69	0.90	0.89	110	84

LEED-NC & LEED-EB Credits – White DFP60 alone can obtain 1 credit in either U.S. Green Building Council's LEED-NC or LEED-EB programs. In combination with other design criteria the membrane may help attain many other credits.

LEED CREDITS	
LEED-NC Credit Category	Duro-Last Attribute
Sustainable Sites Heat Island Reduction	Solar Reflective Index (SRI) = 110
LEED-EB Credit Category	Duro-Last Attribute
Sustainable Sites Heat Island Reduction	Solar Reflective Index (SRI) = 110

WARRANTY:

The following warranties are available for projects utilizing DFP60. Contact Duro-Last for warranty details.

AVAILABLE WARRANTIES					
Supreme	15-Year NDL Warranty	20-Year NDL Warranty – 15 Years Consequential Damages And 5 Years Material		20-Year NDL Warranty – 15 Years Consequential Damages And 5 Years Material and Labor	
		15-Year NDL Hail Warranty ¹	15-Year NDL Hail & High Wind Warranty ¹	15-Year NDL High Wind Warranty ¹	20-Year NDL High Wind Warranty ¹
Basic	15-Year NDL Warranty ¹	20-Year NDL Warranty ¹		25-Year NDL Warranty ^{1, 2}	
Residential	15-Year Residential Material Limited Warranty ¹			20-Year Residential Material Limited Warranty ¹	

¹ Excludes consequential damage coverage.

² Refer to the 25 and 30-Year Warranty Requirements for additional installation criteria.

CODES AND STANDARDS:

Underwriters Laboratories (US & Canada), UL Evaluation Report (ER10128), FM Approvals, Canadian Construction Materials Centre (CCMC 13695-L), State of Florida, Miami-Dade County, Texas Department of Insurance.

STORAGE:

Store rolls lengthwise on pallets. Use tarps to keep rolls dry.

MEMBRANE ATTACHMENT:

Adhered – DFP60 may be adhered to a variety of roof decks, walls, cover boards and insulations. It may be adhered directly to an existing built-up roof (BUR) by using approved membrane adhesives. Adhesion pull tests are required prior to adhering to BUR. The tests must be performed on a 1 x 1-foot area and receive minimum values of 150 pounds per square foot. Refer to the Adhered Duro-Fleece Roofing System Specification for substrate preparation, acceptable adhesives and system requirements.

Mechanically Fastened – DFP60 may be mechanically fastened to a variety of roof deck and wall materials. An appropriate slip sheet, insulation or cover board may be required. Refer to the Roll Good Mechanically Fastened Roofing System Specification for system requirements.

PHYSICAL PROPERTIES:

DFP60 has been subjected to the tests required by ASTM D4434 “Standard Specification for Poly (Vinyl Chloride) Sheet Roofing” and has been classified as a Type III, internally reinforced sheet with a fabric backing. DFP60 also meets or exceeds all ASTM D4434 Type II and Type IV requirements.

The results of each test are listed below. ASTM’s Overall Thickness requirements for the membrane are plus or minus 10% (nominal) of the listed Typical Value.

DFP60 PHYSICAL PROPERTIES				
Physical Property	Test Method	ASTM D4434 Requirement	Result	Typical Value
Overall Thickness	ASTM D751	≥ 0.054 and ≤ 0.066 in. (≥ 54 and ≤ 66 mil)	PASS	0.060 in. (60 mil), nominal (With fleece: 90 mil)
Thickness Over Scrim	ASTM D7635	≥ 0.016 in.	PASS	0.032 in. (32 mil)
Breaking Strength ¹	ASTM D751 Grab Method	≥ 200 lbf./in.	PASS	546 x 490 lbf./in.
Elongation ¹	ASTM D751 Grab Method	≥ 15%	PASS	20% x 39%
Seam Strength	ASTM D751 Grab Method	≥ 409 lbf. (75% of Breaking Strength)	PASS	539 lbf.
Tear Strength ¹	ASTM D751 Procedure B	≥ 45 lbf.	PASS	104 x 192 lbf.
Low Temp. Bend	ASTM D2136	Must pass at -40° F	PASS	PASS
Heat Aging	ASTM D3045	Conditioned for 56 days in oven maintained at 176° F	PASS	PASS
Accelerated Weathering	ASTM G155	10,000 hours total test time. Irradiance level of 0.35 W/m ² -340nm. Cycle: 102 minutes light, 18 minutes light + H ₂ O spray, 63±2.5° C black panel, 30±5% RH	PASS	PASS
Dimensional Stability ¹	ASTM D1204	Conditioned for 6 hours in oven maintained at 176° F. Allowable change: ≤ 0.5%	PASS	0.15% x 0.15%
Water Absorption	ASTM D570	Immersed in water at 158° F for 168 hours. Allowable weight change: ≤ 3%	PASS	2.1%
Static Puncture	ASTM D5602	≥ 33 lbf.	PASS	PASS
Dynamic Puncture	ASTM D5635	≥ 14.7 ft-lbf.	PASS	PASS

¹ Typical values are shown for both machine and cross machine directions. The machine direction results are listed first.

ADDITIONAL TESTS		
Fungi Resistance	ASTM G21	No Sustained Growth or Discoloration
Moisture Vapor Transmission	ASTM E96, Proc. B, Method A	< 0.35 U.S. perms



Duro-Last, the “World’s Best Roof”, Duro-Fleece Plus, and Duro-Fleece are trademarks in the Amrize portfolio. All other trademarks are property of their respective owners.