

# SOPRAMASTIC

## DESCRIPTION:

Sopramastic is a black, solvent-based mastic containing SBS modified bitumen, fibers and mineral fillers. Sopramastic has been formulated with a high level of polymer in order to resist flow at high temperatures and is easily manipulated at temperatures down to 14° F.

Sopramastic is an ideal complement for the Duro-Last® Vapor Barrier when used together to form a temporary roof assembly. Its uses include waterproofing of T joints, transitions and any other openings within a Duro-Last Vapor Barrier temporary roof assembly.

## ORDERING:

Sopramastic is ordered individually or in cases of 20.

- 10.5-ounce tube (Item #1346)

## STORAGE AND HANDLING

Product can be stored for up to 12 months in original sealed containers. Store in a cool, dry area.

**Product is flammable. Keep away from open flames.**

## PRECAUTIONS:

1. Read Safety Data Sheets (SDS) prior to using.
2. Wear proper personal protective equipment, such as gloves and eye protection, per the SDS.
3. **This product is not intended for use with any Duro-Last membrane.**

## INSTALLATION:

1. Limitations
  - a. The minimum ambient and surface temperature before application should be 14° F and rising.
  - b. Apply to a clean and structurally sound substrate.



2. When Duro-Last Vapor Barrier is used as a temporary roof, apply Sopramastic at all T joints, transitions, and openings with a standard cartridge extruder gun. Sopramastic is not required if the Duro-Last Vapor Barrier is immediately covered by a complete roof assembly. **Sopramastic can be applied to damp surfaces.**
3. Reference detail drawings for more information.

TABLE 1. PHYSICAL PROPERTIES <sup>1,2</sup>		
	Standards	Results
Specific gravity at 68° F	-	1.12 kg/L
Color	-	Black
Application temperature range	-	14 to 95° F
Service temperature range	-	-40 to 175° F
Solids by weight	-	83%
Set time	-	Between 4 and 24 hours, depending on temperature and quantity applied.

<sup>1</sup> All values are nominal.

<sup>2</sup> Meets the requirements of CAN/CGSB-37.5-M89 and ASTM D4586 standards.

## CLEANING:

Tools can be cleaned with petroleum solvents such as mineral spirits, Varsol™, xylene, etc. Do not allow cleaning solvents to come in contact with any Duro-Last membrane.