

# DURO-LAST® VB PRIMER

## DESCRIPTION:

Duro-Last® VB Primer is a solvent-based primer composed of a blend of natural resins and synthetic rubber. Duro-Last VB Primer is designed to enhance the adhesion of Duro-Last Vapor Barrier to a variety of surfaces such as structural concrete, gypsum, lightweight concrete, wood, and masonry.

## ORDERING:

Duro-Last VB Primer is ordered in individual 5-gallon pails.

- 33-lb. pail (Item #1345)

## STORAGE AND HANDLING

Product can be stored for up to 36 months in original sealed containers. Store in a cool, well-ventilated area between 14 and 75° F. Keep away from any source of heat, dampness, humidity, oxidizing agents or direct sunlight.

**Product is flammable prior to curing. Keep away from open flames and any other source of ignition.**

## PRECAUTIONS:

1. Read Safety Data Sheets (SDS) prior to using.
2. Wear proper personal protective equipment, such as gloves and eye protection, per the SDS.
3. **This product is not intended for use with any Duro-Last membrane.**

## INSTALLATION:

1. Limitations
  - a. The minimum ambient and surface temperature before application should be 14° F and rising.
  - b. Apply to a clean and structurally sound substrate.
2. Shake product thoroughly prior to application.
3. Apply to deck at a rate of 75 – 125 sq. ft. per gallon using either a brush or roller.
4. Do not install Duro-Last Vapor Barrier until Duro-Last VB Primer has completely dried. **Do not accelerate drying by use of heat.**



DURO-LAST VB PRIMER	
Specific gravity at 68° F	6.59 lbs./gal <sup>1</sup>
Solids by weight	24% <sup>1</sup>
Viscosity, Brookfield at 77° F	200 cP <sup>1</sup>
Set time	Between 15 and 60 minutes, depending on temperature and quantity applied.
Application temperature	14° F and rising
Coverage	75 – 125 sq. ft. per gallon

<sup>1</sup> Nominal.

## CLEANING:

Tools can be cleaned with petroleum solvents such as mineral spirits, Varsol™, xylene, etc. **Do not allow cleaning solvents to come in contact with any Duro-Last membrane.**