



DURO-GUARD® PRODUCT WEIGHT CHART

(Pounds Per Square Foot)

Product Thickness	ISO HD & ISO HD-MA	DensDeck® & DensDeck Prime	Securock® Glass-Mat	Securock Gypsum-Fiber	DEXcell® Glass Mat & FA Glass Mat	DEXcell Cement Roof Board	EVERBOARD™ Roof Board	EPS Fan Fold	XPS Fan Fold
1/4"		1.20	1.20	1.57	1.20		1.25		
3/8"				1.96					0.080
7/16"						2.10			
1/2"	0.343	2.00	2.00	2.76	2.00		2.00	0.055	
5/8"		2.50	2.70	3.20	2.50				

	EPS Type I	EPS Type II	EPS Type VIII	EPS Type IX	ISO II	ISO III
1.0"	0.083	0.125	0.104	0.167	0.245	0.315
1.1"	0.091	0.138	0.114	0.184	0.259	0.329
1.2"	0.100	0.150	0.125	0.200	0.272	0.342
1.3"	0.108	0.163	0.135	0.217	0.286	0.356
1.4"	0.116	0.175	0.146	0.234	0.299	0.369
1.5"	0.125	0.188	0.156	0.251	0.313	0.383
1.6"	0.133	0.200	0.166	0.267	0.326	0.396
1.7"	0.141	0.213	0.177	0.284	0.340	0.410
1.8"	0.149	0.225	0.187	0.301	0.353	0.423
1.9"	0.158	0.238	0.198	0.317	0.367	0.437
2.0"	0.166	0.250	0.208	0.334	0.380	0.450
2.1"	0.174	0.263	0.218	0.351	0.394	0.464
2.2"	0.183	0.275	0.229	0.367	0.407	0.477
2.3"	0.191	0.288	0.239	0.384	0.421	0.491
2.4"	0.199	0.300	0.250	0.401	0.434	0.504
2.5"	0.208	0.313	0.260	0.418	0.448	0.518
2.6"	0.216	0.325	0.270	0.434	0.461	0.531
2.7"	0.224	0.338	0.281	0.451	0.475	0.545
2.8"	0.232	0.350	0.291	0.468	0.488	0.558
2.9"	0.241	0.363	0.302	0.484	0.502	0.572
3.0"	0.249	0.375	0.312	0.501	0.515	0.585
3.1"	0.257	0.388	0.322	0.518	0.529	0.599
3.2"	0.266	0.400	0.333	0.534	0.542	0.612
3.3"	0.274	0.413	0.343	0.551	0.556	0.626
3.4"	0.282	0.425	0.354	0.568	0.569	0.639
3.5"	0.291	0.438	0.364	0.585	0.583	0.653
3.6"	0.299	0.450	0.374	0.601	0.596	0.666
3.7"	0.307	0.463	0.385	0.618	0.610	0.680
3.8"	0.315	0.475	0.395	0.635	0.623	0.693
3.9"	0.324	0.488	0.406	0.651	0.637	0.707
4.0"	0.332	0.500	0.416	0.668	0.650	0.720
4.1"	N/A	0.513	0.426	0.685	0.664	0.734
4.2"	N/A	0.525	0.437	0.701	0.677	0.747
4.3"	N/A	0.538	0.447	0.718	0.691	0.761
4.4"	N/A	0.550	0.458	0.735	0.704	0.774
4.5"	N/A	0.563	0.468	0.752	0.718	0.788

Duro-Last, "World's Best Roof" and Duro-Guard are registered trademarks owned by Duro-Last, Inc. DensDeck is a registered Trademark owned by Georgia-Pacific Gypsum LLC. Securock is a registered Trademark owned by USG Corp. DEXcell is a registered Trademark owned by National Gypsum Co.

Created: 09/04/2015 Revised: 03/18/2017, 11/02/2018, 05/20/2019, 12/04/2019, 01/21/2020, 08/19/2020, 10/11/2021